Optimization of Electrode Materials for Lithium-Ion and Sodium-Ion Batteries in Electric Vehicles

Jiancheng Kan *

RDFZ Xishan School, Beijing, 100091, China

* Corresponding Author Email: jckan2007@bjzyytonline.com

Abstract. As the electric vehicle (EV) market continues to grow, the demand for high-performance energy storage solutions that enable longer driving ranges, faster charging, and prolonged battery life intensifies. Nanotechnology has emerged as a crucial factor in revolutionizing the development of both lithium-ion and sodium-ion batteries. By engineering electrode materials at the nanoscale, nanotechnology offers significant improvements in ion diffusion, energy density, and cycling stability. This paper investigates the influence of nanomaterials on cathode and anode materials, with a particular focus on enhancing the performance of layered oxides, polyanionic compounds, and silicon-based anodes. A detailed comparative analysis between lithium-ion and sodium-ion battery technologies is conducted, evaluating how nanotechnology can bridge the gap in performance, cost, and resource availability. The challenges related to material costs, safety concerns, and scalability are also discussed, emphasizing the complexities of nanomaterial integration in EV batteries. Despite these obstacles, ongoing research into nanomaterial innovations is expected to play a key role in shaping the future of battery technologies, ensuring they meet the evolving requirements of the EV industry. Future trends and potential breakthroughs in nanomaterials are explored, underscoring their importance in achieving next-generation energy storage solutions.

Keywords: Nanotechnology, lithium-ion battery, sodium-ion battery, electrode material.

1. Introduction

The rise of electric vehicles (EVs) has become central to the global transition to more sustainable transportation systems. This shift is driven not only by the need to reduce greenhouse gas emissions but also by a growing awareness of the limitations of fossil fuel transportation. As EV adoption accelerates, there is increasing pressure on battery technologies to meet the evolving expectations of consumers, industry participants and governments.

One of the key factors driving demand for high-performance energy storage systems for EVs is the need for greater driving range. Consumers expect EVs to match or exceed the range offered by internal combustion engine (ICE) vehicles. This expectation puts significant pressure on battery developers to improve the energy density of batteries to allow EVs to travel farther on a single charge without significantly increasing battery size or weight. In addition, shorter charging times are critical to the widespread acceptance of EVs. Current charging infrastructures must evolve to reduce the time it takes to charge an EV battery, and advances in battery technology are critical to achieving this goal.

Battery life is another key factor influencing the development of energy storage systems. Longer-lasting batteries not only extend the life of EVs but also reduce the environmental and economic costs associated with battery replacement. Nanotechnology has emerged as a promising way to address these challenges. By manipulating materials at the nanoscale, researchers have discovered ways to improve battery performance in ways that were previously unattainable [1]. For example, nanostructured materials can improve the electrochemical properties of cathodes and anodes, leading to faster charging, higher energy density and longer cycle life [2].

Nanotechnology holds particular promise for lithium-ion and sodium-ion battery technologies, which are leading contenders to power the next generation of EVs. Although lithium-ion batteries currently lead the market, sodium-ion batteries present a more abundant and affordable option. Through the use of nanomaterials, both battery types can benefit from improved ion transport, enhanced stability and increased energy density. However, the successful implementation of these

innovations depends on overcoming several significant challenges, including manufacturing scalability, material costs, and long-term stability.

In the following sections, this paper will explore how nanotechnology is driving advances in EV batteries, focusing on the development of cathode and anode materials. It will also provide a comparative analysis of lithium-ion and sodium-ion batteries, examining how nanotechnology can close the performance gap between the two technologies. Finally, challenges and future trends in nanomaterial batteries will be discussed, providing insights into the path forward for the EV industry.

2. Nanotechnology's Impacts on Cathode Materials in EV Batteries

Nanostructure cathode material enhances the surface area, promotes faster ion diffusion, and reduces impedance, resulting in higher charge and discharge rate and improvement of overall electrochemical properties. This is the key to achieving higher energy density and better cycle life.

Sodium-ion batteries are regarded as a more environmentally sustainable option compared to lithium-ion batteries and also gain advantages from nanotechnology. The role of nanostructured layered oxides in enhancing Na^+ diffusion and phase stability is critical for overcoming the slower diffusion kinetics of sodium relative to lithium [3,4]. Nanotechnology has transformed the development of cathode materials for both lithium-ion and sodium-ion batteries, largely by enhancing their energy density. Nanostructured cathodes, composed of materials like layered oxides and polyanionic compounds, improve ion diffusion, which in turn boosts charging capacity [5,6]. One such material, lithium nickel manganese cobalt oxide (NMC), has been extensively studied due to its high specific energy. By introducing nanostructures, these materials exhibit a larger surface area, which contributes to faster ion exchange and improved electrochemical performance. Sodium cathodes, such as sodium manganese oxide, have similarly benefited from nanoscale engineering, which helps overcome the slower diffusion kinetics inherent in larger sodium ions [7]. These advances are critical to realizing the longer driving ranges and faster charging times demanded by consumers for EVs.

3. Improvement of Anode Materials Using Nanotechnology

3.1. Nanotechnology and Low-Cost Anode Materials

Economic and resource factors are crucial when evaluating anode materials for EV batteries, particularly when contrasting lithium-ion and sodium-ion systems. Lithium is comparatively rare and costly, whereas sodium is more plentiful and affordable. This makes sodium a promising candidate for large-scale applications like electric vehicles. Nanotechnology is key to enhancing the performance and lifespan of sodium-ion anodes [8]. Especially the use of nanostructured carbon-based anodes such as hard carbon, offers higher capacity and longer cycle life than conventional sodium-ion anodes [9].

The nanoscale structure improves the material's electrical conductivity and ion transport performance by reducing the size of carbon particles, making it more suitable for large-scale EV applications [10,11]. Research has also focused on optimizing the shape of the carbon anode to improve the storage performance of sodium, which may be achieved through techniques such as electrospinning and stencil, thereby increasing the ion diffusion rate and overall electrochemical efficiency.

3.2. Energy Density and Application Suitability

The energy density of the cathode is a critical factor in the overall performance of EV batteries. Although lithium-ion batteries have historically been preferred due to their high energy density, sodium-ion batteries have typically lagged. However, the development of nanostructured cathode materials like silicon and tin is helping sodium-ion batteries narrow the gap. Silicon, in particular, has a significantly higher theoretical capacity compared to graphite, which has been widely used in

lithium-ion batteries [12]. However, its volume expansion during cycling poses a significant challenge. Nanotechnology addresses this issue by creating silicon nanoparticles or nanowires that can accommodate expansion without breaking apart, thereby increasing both energy density and cycle life [13].

4. Comparative Analysis: Lithium-Ion Battery and Sodium-Ion Battery

4.1. Cost and Resource Availability

The economic and environmental sustainability of battery materials is a key consideration for the future development of EVs. Lithium-ion batteries, while superior in performance, rely on scarce and expensive materials such as lithium and cobalt. In contrast, sodium-ion batteries use sodium, which is an abundant and inexpensive resource. Nanotechnology can help sodium-ion batteries become more competitive by improving their energy density and charging capacity, narrowing the performance gap between the two technologies. In addition, the lower cost of sodium-ion batteries makes them more attractive in applications where price is a major consideration, such as mass-market EVs or grid storage systems.

4.2. Effect of Nanostructured Electrode Materials on Electrochemical Performance of Lithium-Ion Batteries

Battery technology is vital for clean energy systems as it aids in lowering greenhouse gas emissions. To achieve high power and energy density in lithium-ion batteries, advancements in cathode, anode, and electrolyte materials are essential. The electrochemical performance (including cyclic stability, power density, and reversibility) is influenced by the morphology and composition of the electrode materials, which can be controlled during the synthesis and annealing processes. The development of nanostructured electrode materials offers significant benefits. Nano-sized electrodes exhibit minimal impedance growth, which reduces power loss during the charge and discharge cycles.

Additionally, the increased surface area between the electrode and electrolyte enhances the charge and discharge rates, maximizing power output. Nanostructured lithium manganese phosphate ($LiMnP_4$) is a promising material for improving lithium-ion battery performance. The integration of nanoscale features enhances thermal stability and electrochemical behavior, thereby directly boosting energy density.

4.3. Electrochemical Properties

Li-ion batteries have been widely commercialized due to their high energy density, efficiency, and ability to undergo multiple charge-discharge cycles [14]. The main electrochemical mechanism in lithium-ion batteries is the movement of lithium ions between the cathode and anode via the electrolyte during charge and discharge cycles. Similarly, sodium-ion batteries function based on the same principle, where sodium ions travel between the electrodes. While sodium is more abundant and cheaper than lithium, it also has larger ionic radii (102 pm for Na^+ compared to 76 pm for Li^+). This larger size affects the mobility of sodium ions within the battery and results in lower energy density compared to Li-ion batteries. Nonetheless, Na-ion batteries are less prone to overheating and thermal runaway, potentially making them safer for large-scale applications.

4.4. Availability and Sustainability

Lithium is a relatively scarce element, with major deposits located in regions such as South America and Australia. The mining and extraction of lithium can have significant environmental impacts, including water consumption and ecosystem disruption. In contrast, sodium is one of the most abundant elements on Earth, and its extraction has a much lower environmental footprint.

The sustainability of battery technology is becoming increasingly important as the world transitions to renewable energy [15]. Na-ion batteries, due to the widespread availability of sodium

and the use of more environmentally friendly electrode materials, may have an advantage in terms of long-term sustainability. Moreover, the potential for lower costs due to the abundance of sodium makes Na-ion technology particularly appealing for grid-scale energy storage applications.

4.5. Future Prospects and Challenges

While Li-ion batteries will likely remain the dominant energy storage technology for the foreseeable future, the development of Na-ion batteries represents a significant advancement. Researchers are working to overcome the current limitations of Na-ion technology, including improving energy density, cycle life, and efficiency.

A key challenge for sodium-ion batteries is the development of improved electrode materials that can handle the larger sodium ions while maintaining energy density. Furthermore, enhancing electrolytes and optimizing cell design are essential steps to boost the overall performance of sodium-ion batteries.

Due to the abundance and affordability of sodium, sodium-ion batteries are expected to become important in applications where cost-effectiveness and sustainability take precedence over energy density, such as in large-scale energy storage for the grid and stationary power systems.

4.6. Electrode Activation Process and Li-ion Intercalation Mechanism

During the initial charging cycle, electrodes made from lithium-rich and manganese-rich materials must undergo an activation step by charging beyond 4.5 V to reach high capacity [16]. The initial charging voltage curve depicted in Fig. 1A demonstrates the relationship between the position of the lithium-ion interlayer and the redox center, as observed through in-situ X-ray diffraction (XRD) and X-ray absorption spectroscopy (XAS). This occurs during the first charging process of lithium-rich and manganese-rich materials. The oxidation reaction of $Ni^{2+/4+}$ and $Co^{3+/4+}$ occurs, which is consistent with the behavior of standard Li [NiaCobMnc]O_2 layered material [17]. Subsequently, a longer activation voltage platform appeared at about 4.5 V, which involved the release of oxygen, the formation of the surface spinel phase and the extraction of lithium ions from the transition metal layer. At a higher potential, the anionic oxidation reaction of oxide O^{2-} is found, and this process is accompanied by the phenomenon of transition metal migration to the lithium layer, which is located between the O^{2-} sheet layer that is not shielded after excessive lithium-ion extraction. This transition metal migration will lead to resistance to the re-layering of lithium ions and cause a large voltage lag between charge and discharge. During the discharge process, as shown in the differential capacity diagram shown in Fig. 1B, lithium ions first enter the transition metal layer, combine with O^{2-x}, Ni^{4+} and Co^{4+}, and are accompanied by manganese reduction. Then, lithium ions are inserted into the lithium layer while further reducing manganese.




Figure 1. (A) Charge and (B) d*Q*/d*V* profiles for the first cycle of a representative Li-rich $0.35LiMn_2O_3 \cdot 0.65Li[Mn_{0.45}Ni_{0.35}Co_{0.20}]O_2$ electrode in a Li-cell at a rate of C/20, 30°C [18].

5. Conclusion

Nanotechnology has become a transformative force in the development of battery materials for EVs. By manipulating materials at the nanoscale, researchers have been able to make significant advances in cathode and anode performance, leading to the development of batteries with higher energy density, greater durability, and faster charging speeds. Nanostructured cathodes, such as those made of layered oxides and polyanionic compounds, achieve better ion diffusion and higher charging capacity, while advancements in anode materials, particularly through the use of silicon nanoparticles and hard carbon, improve the energy density and cycle life of batteries.

The comparative analysis of lithium-ion and sodium-ion batteries highlights the potential of sodium-ion technology to become a more cost-effective and sustainable alternative to lithium-ion batteries, especially as nanotechnology continues to advance. However, challenges remain in bringing these innovative technologies to mass production, ensuring safety and reducing material costs. Continued research and investment in nanomaterials are essential to overcome these barriers and fully realize the potential of nanotechnology in EV batteries.

As the EV industry continues to evolve, nanotechnology will play a key role in shaping the future of energy storage systems. The technological advances discussed in this article are only the beginning of the possibilities, and further breakthroughs may occur as researchers explore new materials and technologies. Ultimately, the commercialization of nanotechnology-based batteries will be key to meeting the growing demand for high-performance, sustainable energy storage solutions for EVs.

References

[1] Pitchai Ragupathy, Thavasi Venkatesan, Mhaisalkar Subodh G., et al. Nanostructured cathode materials: a key for better performance in Li-ion batteries. Journal of Materials Chemistry, 2011, 21 (30): 11040 - 11051.

[2] Tang Jianming and Yamauchi Yusuke. MOF morphologies in control. Nature Chemistry, 2016, 8 (7): 638 - 639.

[3] Chen Xiaoqin, Wang Chenkai, Wang Yongxin, et al. Recent progress in layered oxide cathodes for sodium-ion batteries: Stability, phase transition, and solutions. Journal of Materials Chemistry A, 2024, https: //doi.org/10.1039/D4TA03372H.

[4] Pan Huilin, Hu Yong-Sheng and Chen Liquan. Room-temperature stationary sodium-ion batteries for large-scale electric energy storage. Energy & Environmental Science, 2013, 6 (8): 2338 - 2360.

[5] Martha Suresh Kumar, Markovsky Boris, Grinblat Jan, et al. LiMnPO4 as an advanced cathode material for rechargeable lithium batteries. Journal of Electrochemical Society, 2009, 156 (7): A541 - A552.

[6] Ohzuku Tsutomu and Ueda Atsushi. Solid-state redox reactions of LiCoO2 for 4-volt secondary lithium cells. Journal of The Electrochemical Society, 1994, 141 (11): 2972 - 2977.

[7] Palomares Verónica, Casas-Cabanas Montse, Castillo-Martínez Elizabeth, et al. Update on Na-based battery materials. Energy & Environmental Science, 2013, 6 (8): 2312 - 2337.

[8] Xu Jing, Lin Feng, Doeff Marca M., et al. A review of Ni-based layered oxides for rechargeable Li-ion batteries. Journal of Materials Chemistry A, 2017, 5 (3): 874 - 901.

[9] Wenzel Sebastian, Hara Takeshi, Janek Jürgen, et al. Room-temperature sodium-ion batteries: Improving the rate capability of carbon anode materials. Energy & Environmental Science, 2011, 9 (4): 3342 - 3345.

[10] Li Xing, Zheng Jianming, Ren Xiaodi, et al. Dendrite-free and performance-enhanced lithium metal batteries through optimizing solvent compositions and adding combinational additives. Advanced Energy Materials, 2018, 8 (15): 1703022.

[11] Erickson Evan M., Schipper Florian, Penki Tirupathi Rao, et al. Recent advances and remaining challenges for lithium-ion battery cathodes. Journal of Electrochemical Society, 2017, 164 (1): A6341.

[12] He Yang, Piper Daniela Molina, Gu Meng, et al. In situ transmission electron microscopy observation of pulverization of amorphous Si and SiO2 coated Si nanoparticles for lithium-ion battery anodes. ACS Nano, 2014, 8 (11): 11816 - 11823.

[13] Wu Hui, Chan Gerentt, Choi Jang Wook, et al. Stable cycling of double-walled silicon nanotube battery anodes through solid–electrolyte interphase control. Nature Nanotechnology, 2012, 7 (5): 310 - 315.

[14] Blomgren George E. The development and future of lithium-ion batteries. Journal of the Electrochemical Society, 2016, 164 (1): A5019.

[15] Hwang Jang-Yeon, Myung Seung-Taek and Sun Yang-Kook. Sodium-ion batteries: present and future. Chemical Society Reviews, 2017, 46 (12): 3529 - 3614.

[16] Gao Keke, Sun Chunwen and Wang Zelin. Recent advances in high-performance lithium-rich manganese-based materials for solid-state lithium batteries. Materials Chemistry Frontiers, 2024, 8: 3082 - 3105.

[17] Cho Jung Sang, Park Jin-Sung and Kang Yun Chan. Porous FeS nanofibers with numerous nanovoids obtained by Kirkendall diffusion effect for use as anode materials for sodium-ion batteries. Nano Research, 2017, 10: 897 - 907.

[18] Schipper Florian, Nayak Prasant Kumar, Erickson Evan M., et al. Study of cathode materials for lithium-ion batteries: recent progress and new challenges. Inorganics, 2017, 5 (2): 32.