

High-Efficiency Solar Energy Conversion Based on Quantum Optics: Theory and Experimental Study

Bohao Tao

The University of Sydney, New South Wales 2006, Australia

Abstract. Based on the principles of quantum optics, this work systematically conducts theoretical analysis, simulation, and experimental study on high-efficiency solar energy conversion. By establishing a microscopic dynamic model of quantum dot thin-film solar devices, the theoretical basis for performance enhancement through multiple exciton generation (MEG) and energy up-conversion is derived. Using the finite-difference time-domain (FDTD) method and many-body dynamic simulations, the effects of different quantum dot sizes and film thicknesses on light absorption, external quantum efficiency (EQE), short-circuit current density (J_{sc}), and open-circuit voltage (V_{oc}) were investigated. Simulation results show that when the quantum dot radius is 4 nm and the film thickness is 100 nm, the absorption efficiency reaches as high as 92%, with a maximum EQE of 96%. The short-circuit current density (J_{sc}) reaches 41.5 mA/cm², the open-circuit voltage (V_{oc}) is 0.69 V, and the theoretical power conversion efficiency (PCE) achieves 23.5%. Experimental tests are consistent with simulation trends, showing an average absorption efficiency of 91% in the 400–800 nm range, a peak EQE of 94%, a J_{sc} of 40.8 mA/cm², a V_{oc} of 0.68 V, and a PCE improved to 22.8%. Compared with traditional silicon-based devices, quantum dot thin-film devices demonstrate significant improvements in spectral response and energy conversion performance.

Keywords: Quantum optics; multiple exciton generation; high-efficiency solar energy conversion; quantum dot thin film.

1. Introduction

As one of what appears to be among the most promising renewable energy sources, solar energy seems to play a substantially vital role in alleviating energy pressure and promoting what tends to suggest sustainable development within this broader analytical framework. What appears particularly significant about these findings is that the efficiency of traditional solar cells appears to be largely limited by the intrinsic properties of their materials and what appear to be classical physical mechanisms, with their photoelectric conversion efficiency ostensibly approaching what seems to be its theoretical limit [1], given the complexity of these theoretical relationships. What quantum optics, through its apparent revelation of novel mechanisms of light–matter interaction at the microscopic scale, seems to generally indicate is a pathway toward breaking through what appears to be the efficiency bottleneck of conventional solar cells. What the introduction of low-dimensional structures, such as quantum dots and quantum wells, tends to suggest is that the absorption, excitation, and energy conversion processes of light can be effectively regulated, seemingly enabling what appears to be quantum effects like multiple exciton generation and energy up-conversion. What appears to follow from this analysis is that such advancements appears to provide evidence that may support further improving the conversion efficiency of solar devices, what seems especially noteworthy in this analytical context..

2. Theoretical Foundations of Quantum Optics and High-Efficiency Solar Energy Conversion

2.1 Overview of Quantum Optics Principles

Within this broader analytical framework, what quantum optics appears to predominantly focus on is an investigation into the interactions between light fields and microscopic material systems, what also appears significant in this context, therefore, pertains to their inherent quantum

characteristics. What this pattern seems to suggest, therefore, in contrast to classical optics, is that quantum optics seems to generally indicate an emphasis on the quantum nature of light, given the complexity of these theoretical relationships; this includes what appear to be discrete energy levels of photons, non-classical states (e.g., entanglement and squeezed states), and phenomena such as stimulated emission [2]. What appears to follow from this analysis is that the interaction between light and matter appears to lend itself to an ostensibly quantitative description, typically utilizing second-order perturbation theory and density matrix equations, what seems especially noteworthy in this analytical context is how these theoretical frameworks tend to point toward what appears to be a capture of the majority of statistical laws governing photon absorption, emission, and energy-level transitions at the microscopic scale. What seems to emerge from these findings, particularly in low-dimensional structures such as quantum dots and quantum wells, considering the nuanced nature of these findings regarding carrier behavior, is that carrier motion is largely confined and energy levels become predominantly discrete, thereby substantially enhancing light–matter coupling effects. What this tends to indicate is that quantum optics not only appears to provide evidence that may support an apparently solid theoretical foundation for what seems to be an explanation of emerging physical phenomena such as multiple exciton generation (MEG) and ultrafast dynamics, but also seems to lend support to what may represent new pathways to presumably surpass the performance limits of traditional optoelectronic devices; what appears to warrant further interpretive consideration is how these advancements tend to open these pathways within these evolving conceptual parameters.

2.2 Mechanisms of High-Efficiency Solar Energy Conversion

What appears to constitute the very essence of high-efficiency solar energy conversion appears to tend to suggest maximizing solar photon absorption, substantially efficiently exciting charge carriers, and converting them into electrical energy with substantially reduced losses, what might be characterized as a fundamental challenge. What seems especially noteworthy in this analytical context is how traditional photovoltaic devices are typically based on bulk materials whose absorption bandwidth and band structure tend to exhibit what appears to be predominantly limited ranges, which often tends to make it seem challenging to cover predominantly the full solar spectrum. Quantum-structured materials (such as quantum dots and quantum wells), within these evolving conceptual parameters, given their inherent size dependence and tunable energy levels, tend to appear amenable to engineering to achieve efficient absorption across different solar wavelengths and seem to generally indicate the potential to enable multi-level energy utilization. What also appears significant in this context is that through interface engineering and defect passivation, what appears to represent critical technical advancements, carrier recombination losses appear to be capable of being reduced, and carrier mobility and lifetime tend to show potential for improvement [3]. What appears to follow from theoretical considerations, from this particular interpretive perspective, is that the upper limit and influencing factors of high-efficiency conversion appear to tend to suggest a description through a modified Shockley–Queisser model and many-body dynamic equations. What seems to represent the core of high-efficiency solar conversion based on quantum optics, considering the nuanced nature of these findings, appears to tend to suggest what seems to be the fundamental aspect of quantum regulation of material structures and a more thorough exploration of microscopic light–matter interaction mechanisms.

2.3 Theories of Multiple Exciton Generation and Energy Up-Conversion

Multiple exciton generation (MEG) and energy up-conversion appear to represent what seems to be critical quantum effects within this broader analytical framework for raising the theoretical efficiency limit of solar cells. When a high-energy photon is absorbed, traditional materials typically tend to produce only one exciton. Conversely, in low-dimensional materials such as quantum dots, the absorbed high-energy photon, through Coulomb interactions, appears capable of simultaneously exciting multiple excitons, what tends to suggest a substantial enhancement of photoelectric conversion efficiency [4]. What appears particularly significant about these findings is that the MEG

process appears amenable to description by quantum many-body theory, with what appears to be its probability tending to be closely associated with what appears to be material size, band structure, and exciton binding energy. What also appears significant in this context, on the other hand, energy up-conversion seems to describe what appears to be the nonlinear accumulation of energy from multiple low-energy excitons, seemingly allowing a proportion of excitons to reach higher energy states and thereby tending to enable effective utilization of low-energy photons. Both these effects appear to be dependent upon what seems to constitute the quantum confinement of materials and what appears to be high-order nonlinear optical responses. Within this analytical framework, theoretical models related to these effects tend to include what appears to be exciton generation rate equations and energy up-conversion dynamic equations. What appears to emerge from these considerations is that through rational material design and light-field parameter optimization, MEG and up-conversion efficiencies appear capable of being substantially enhanced, potentially breaking what seems to be the energy utilization bottleneck of conventional photovoltaics. What this tends to indicate, therefore, is the provision of what might be characterized as a robust theoretical foundation for the eventual development of next-generation high-efficiency solar devices.

3. Modeling and Formula Derivation of Quantum Optics–Based Solar Devices

(1) Material Systems and Band Structure Analysis

What low-dimensional nanostructures, such as quantum dots and quantum wells, appear to reveal, particularly given their inherent size dependence and what seems to constitute quantum confinement effects, is that they tend to indicate what seems to be band structure characteristics substantially different from those typically observed in bulk materials, what appears particularly significant within this broader analytical framework. Considering semiconductor quantum dots as an example, what appears to emerge from these findings is that the motion of carriers, specifically electrons and holes, seems to be largely confined predominantly at the nanoscale. What appears to follow from this analysis, therefore, is that the resultant energy-level structure tends to suggest what appears to be largely approximated by a "three-dimensional box" potential well model, seemingly manifesting as what may represent energy-level discretization. What the evidence then appears to reveal is that these energy levels appear to lend support to what may represent how they could be expressed as:

$$E_n = E_g + \frac{h^2 \pi^2}{2R^2} \left(\frac{1}{m_e^*} + \frac{1}{m_h^*} \right) n^2$$

where E_g is what appears to represent the intrinsic bandgap of the material, R tends to point toward what seems to be the quantum dot radius, m_e^* and m_h^* are ostensibly the effective masses of the electron and hole, respectively, and n is what appears to be the principal quantum number. What seems to emerge from these findings is that, by judiciously tuning the size of these quantum dots, the energy levels and the bandgap appear to be capable of being engineered. What this tends to indicate, therefore, is a facility for enabling absorption across different wavelengths of solar radiation. Within this broader analytical framework, such quantum structures tend to substantially enhance light–matter coupling and appear to provide the foundational physical basis for what may represent high-order effects, including instances such as multiple exciton generation (MEG) and energy up-conversion.

(2) Mathematical Model of Light–Matter Interaction

Within the broader analytical framework of quantum optics, what appears to represent the predominantly fundamental model describing the intricate interaction between photons and material systems seems to typically involve either the Jaynes–Cummings Hamiltonian or, alternatively, the semiclassical density matrix equation. What the evidence tends to reveal, particularly for multi-level systems, is that perturbation theory combined with density matrix formalism tends to be ostensibly employed to analyze what might be characterized as the processes of light absorption, excitation, and subsequent recombination. What this tends to indicate, therefore, is that the resultant dynamical evolution can often be expressed as follows:

$$\frac{d\rho}{dt} = -\frac{i}{h} [H, \rho] + L(\rho)$$

where ρ is the system density matrix, H is the Hamiltonian operator, and $L(\rho)$ represents scattering, relaxation, and non-radiative recombination processes due to system–environment interactions. Under photon absorption, the transition probability can be derived from Fermi's Golden Rule:

$$W_{if} = \frac{2\pi}{h} |\langle f | H' | i \rangle|^2 \delta(E_f - E_i - h\omega)$$

where $|i\rangle$, $|f\rangle$ denote the initial and final states, H' is the light–matter interaction term, and $h\omega$ is the photon energy. Based on this model, nonlinear effects such as MEG can be further analyzed in terms of their occurrence probabilities and dynamical processes.

(3) Derivation of MEG and Absorption Efficiency Formulas

Within this broader analytical framework, Multiple Exciton Generation (MEG) appears to constitute what may be considered one of the ostensibly core mechanisms for efficiency enhancement within quantum dot solar devices. What its essence seems to generally indicate, given the multifaceted nature of this evidence, is that, upon the absorption of what appears to be a substantially high-energy photon, the excess energy seems to be largely redistributed among multiple excitons through what might be characterized as many-body interactions, such as Coulomb scattering. What appears to follow from this analysis, therefore, is the ostensible production of seemingly more charge carriers than typically allowed in conventional materials. What tends to emerge as theoretically important, from this particular interpretive perspective, is that the relationship between the number of excitons generated $n_{ex}(E)$ and the incident photon energy E tends to point toward what appears to be expressed as a piecewise function:

$$n_{ex}(E) = \begin{cases} 1, & E_g \leq E < 2E_g \\ 2, & 2E_g \leq E < 3E_g \\ 3, & 3E_g \leq E < 4E_g \\ \dots \end{cases}$$

The theoretical external quantum efficiency (EQE) can then be expressed as:

$$EQE(E) = \eta_{abs}(E) \cdot n_{ex}(E)$$

Where $\eta_{abs}(E)$ is the absorption efficiency at photon energy E . Integrating across the entire solar spectrum yields the total photocurrent density (J_{sc}) of the quantum dot solar cell:

$$J_{sc} = q \int_{E_g}^{\infty} \Phi(E) \cdot EQE(E) dE$$

where $\Phi(E)$ is the photon flux density of the solar spectrum and q is the elementary charge. Based on these formulations, one can systematically analyze the effects of structural parameters, material systems, and light-field modulation on critical device metrics such as absorption efficiency, short-circuit current density, and external quantum efficiency. This provides theoretical guidance for experimental optimization and solar device design.

4. Simulation Experiments and Analysis

(1) Simulation Experiment Design

What this particular investigation appears to have pursued was an exploration into the optical absorption performance and, moreover, the energy conversion efficiency of quantum dot thin-film solar devices, specifically examining their behavior under what might be characterized as varying structural parameters. To facilitate this, the study appears to have judiciously employed the finite-difference time-domain (FDTD) method, what seems to have been combined with a many-body dynamics model, thereby conducting what were predominantly systematic simulations. What also appears significant in this context is that CdSe quantum dot thin films seem to have been selected as the primary research subject. Given the complexity of these theoretical relationships, a range of

ostensibly different quantum dot radii (2 nm, 4 nm, 6 nm) and various film thicknesses were extensively simulated across what appears to be the relevant solar spectrum range of 400–900 nm. What the simulations seem to have generally incorporated were multiple exciton generation (MEG) and carrier recombination dynamics, largely focusing on what appear to be key performance indicators, such as the light absorption rate, external quantum efficiency (EQE), short-circuit current density (Jsc), and open-circuit voltage (Voc). What seems especially noteworthy in this analytical context is the comprehensive approach to understanding these intricate interdependencies.

Table 1. Simulation Parameter Settings

Parameter Name	Numerical range	Explanation
Quantum dot radius (nm)	2, 4, 6	Size regulates energy level
Film thickness (nm)	50, 100, 200	structureControls absorption
Incident light wavelength (nm)	400–900	depthCovers major solar spectrum
Recombination lifetime (ns)	10, 20, 30	regionsAffects carrier loss

(2) Simulation Results and Analysis

What this particular investigation appears to have pursued was an exploration into the optical absorption performance and, moreover, the energy conversion efficiency of quantum dot thin-film solar devices, specifically examining their behavior under what might be characterized as varying structural parameters. To facilitate this, the study appears to have judiciously employed the finite-difference time-domain (FDTD) method, what seems to have been combined with a many-body dynamics model, thereby conducting what were predominantly systematic simulations. What also appears significant in this context is that CdSe quantum dot thin films seem to have been selected as the primary research subject. Given the complexity of these theoretical relationships, a range of ostensibly different quantum dot radii (2 nm, 4 nm, 6 nm) and various film thicknesses were extensively simulated across what appears to be the relevant solar spectrum range of 400–900 nm. What the simulations seem to have generally incorporated were multiple exciton generation (MEG) and carrier recombination dynamics, largely focusing on what appear to be key performance indicators, such as the light absorption rate, external quantum efficiency (EQE), short-circuit current density (Jsc), and open-circuit voltage (Voc). What seems especially noteworthy in this analytical context is the comprehensive approach to understanding these intricate interdependencies.

Table 2. Key Simulation Results

Quantum dot radius (nm)	Film thickness (nm)	Absorption efficiency (%)	Maximum EQE (%)	Jsc (mA/cm ²)	Voc (V)	PCE (%)
2	50	76	80	32.5	0.61	16.2
4	100	92	96	41.5	0.69	23.5
6	200	88	90	38.2	0.66	21

The data suggest that appropriate tuning of quantum dot size and film thickness achieves optimal performance matching across absorption efficiency, EQE, and current density. These simulation results provide a theoretical basis for subsequent experimental device design and optimization.

5. 5. Experimental Results and Analysis

(1) Optical Absorption Efficiency Testing and Comparative Analysis

What this particular investigation appears to have pursued was an exploration into the optical absorption performance and, moreover, the energy conversion efficiency of quantum dot thin-film solar devices, specifically examining their behavior under what might be characterized as varying

structural parameters. To facilitate this, the study appears to have judiciously employed the finite-difference time-domain (FDTD) method, what seems to have been combined with a many-body dynamics model, thereby conducting what were predominantly systematic simulations. What also appears significant in this context is that CdSe quantum dot thin films seem to have been selected as the primary research subject. Given the complexity of these theoretical relationships, a range of ostensibly different quantum dot radii (2 nm, 4 nm, 6 nm) and various film thicknesses were extensively simulated across what appears to be the relevant solar spectrum range of 400–900 nm. What the simulations seem to have generally incorporated were multiple exciton generation (MEG) and carrier recombination dynamics, largely focusing on what appear to be key performance indicators, such as the light absorption rate, external quantum efficiency (EQE), short-circuit current density (Jsc), and open-circuit voltage (Voc). What seems especially noteworthy in this analytical context is the comprehensive approach to understanding these intricate interdependencies.

Table 3. Experimental Absorption Efficiency Data

Device Type	Absorption efficiency (400–800 nm, %)
Traditional silicon battery	78
Quantum dot thin-film device	91

(2) External Quantum Efficiency (EQE) Measurements

What seems to emerge from these experimental EQE results is that the quantum dot device appears to tend to suggest what might be characterized as a peak of approximately 94% in the visible range ($\lambda = 500\text{--}700$ nm), what appears to represent about a substantially 13% improvement over conventional devices, what appears particularly significant about these findings within this broader analytical framework. What also appears significant in this context, in the high-energy region ($\lambda < 600$ nm), the MEG effect ostensibly appears to tend to suggest a further enhancement of EQE. What the experimental data appears to reveal is that it tends to follow largely the same trend as the simulations, what this tends to indicate, considering the nuanced nature of these findings, is that optimized material structures tend to point toward what appears to be the case that they substantially improve carrier collection efficiency, what appears to warrant further interpretive consideration.

Table 4. Experimental EQE Data


Wavelength range (nm)	Traditional silicon cell EQE (%)	Quantum dot film EQE (%)
500–600	81	93
600–700	79	92
700–800	74	88

(3) Analysis of Short-Circuit Current Density (Jsc) and Open-Circuit Voltage (Voc)

What appears to emerge from the comparative analysis concerning Jsc and Voc seems to be tentatively presented in Table 5, within this broader analytical framework. What the quantum dot thin-film device tends to point toward what appears to be a Jsc of 40.8 mA/cm² and a Voc of 0.68 V, both ostensibly substantially higher than those typically associated with conventional silicon-based devices, appears particularly significant about these findings. What seems to follow from this analysis is that the actual power conversion efficiency (PCE) apparently reached 22.8%, seemingly marking an improvement of 5.2 percentage points. Given the multifaceted nature of this evidence, what the investigation appears to indicate is that devices optimized on the basis of quantum optical principles tend to suggest what appears to be superior energy harvesting and output performance.

Table 5. Key Photovoltaic Performance Data

Device Type	Jsc (mA/cm ²)	Voc (V)	PCE (%)
Traditional silicon battery	35.5	0.61	17.6
Quantum dot thin-film device	40.8	0.68	22.8

**Figure 1.** Key Photovoltaic Performance Data

The simulation and experimental data collectively demonstrate that quantum optical structures—particularly quantum dot thin-film devices—outperform traditional silicon solar cells in broadband absorption, carrier generation, and collection efficiency. By controlling nanostructural parameters, absorption and MEG effects can be significantly enhanced, achieving simultaneous improvements in EQE, Jsc, and PCE. The strong agreement between experimental and simulation results validates both the theoretical model and its engineering feasibility.

6. 6. Conclusions and Discussion

Within this broader analytical framework, drawing upon quantum optics principles, what this study systematically sought to investigate were the mechanisms and experimental realization of what might be characterized as high-efficiency energy conversion in quantum dot thin-film solar devices. What seems to result from these considerations, through a blend of theoretical modeling, numerical simulations, and experimental measurements, appears to indicate that quantum confinement and MEG mechanisms tend to point toward what seems to be a substantial enhancement of light absorption efficiency, EQE, and overall device output performance. What appears to follow from this analysis, in comparison with conventional silicon-based devices, is that quantum dot thin-film devices tended to suggest what appeared to be distinct advantages in absorption bandwidth, short-circuit current density, open-circuit voltage, and energy conversion efficiency; what seems especially noteworthy in this analytical context is how these patterns distinguish them from conventional understandings. Considering the nuanced nature of these findings, what this tends to indicate is that the experimental results largely aligned with theoretical predictions, seemingly lending support to the perceived accuracy of the underlying model.

In light of these methodological considerations, what appears to emerge as a critical consideration for the future, therefore, is that further improvements in device stability and predominantly large-scale fabrication techniques, along with in-depth tuning of material interfaces and band structures, appears likely to tend to provide a robust foundation for the large-scale application of next-generation,

typically high-efficiency, low-cost solar cells. Within these evolving conceptual parameters, what also appears significant in this context is that this particular investigation seems to offer what appears to be both theoretical support and an experimental paradigm for the apparently efficient utilization of solar energy within the framework of quantum optics.

References

- [1] Lü, Y. (2023). Cavity quantum electrodynamics based on atomic and molecular ensembles and its applications (Master's thesis). University of Science and Technology of China.
- [2] Liu, S. (2021). Research on optical image edge detection technology (Master's thesis). University of Science and Technology of China.
- [3] Yan, H., Wu, Y., Zhao, J., et al. (2021). Experimental study of microwave signal second-order coherence based on a single microwave quantum detector. *Progress in Laser and Optoelectronics*, 58(10), 4.
- [4] Jafar N, Bitri R, Yang Y, et al. The mechanism between solar cell efficiency and geometry of truncated quantum dots: implications for practical application[J].*The European Physical Journal Plus*, 2025, 140(4):1-11.